



natureplus e.V.

Guideline I 104

Thermal Insulation Composite Systems

Version: 22-05, Feb. 4, 2022

for the awardance of the eco-label

0 Introduction

The International Association for Sustainable Building and Living – natureplus e.V. – has set itself the goal, through the awardance of a quality label (eco-label), of promoting the use of those construction products which are especially suited to achieving the goal of economicsustainability. The three classic pillars of sustainability (the environment, social aspects and the economy) are reflected in natureplus's the three fundamental requirements: the environment, health and functional quality.

Every construction activity encroaches upon the natural environment and is connected with the consumption of limited resources. Our responsibility towards future generations requires us to undertake every effort to reduce these encroachments to the lowest level possible and to limit our use of resources to a necessary minimum. In view of the foreseeable exhaustion of the reserves of fossil fuels, for example, and the dangers to the earth's climate, such an approach is the only possible means to ensure sustainable and socially equitable development. For the building sector this means promoting the use and application of construction products which help to minimize the consumption of fossil fuels and limited resources. It is natureplus's intention to help promote the commercial success of those products which fulfil these demands.

Energy-saving building methods and the avoidance of uncontrolled ventilation facilitates the accumulation of volatile chemical compounds in the interior air that are emitted by building products and the inventory contained within the building. This presents a(n) (avoidable) danger to the health of the occupants. Also, the accretion of chemical contaminants (especially phthalates/plasticisers) from building products on house dust, the increasing use of biocides in everyday products and the dangers posed by mould growth due to negative product characteristics give rise for concern. An increasing proportion of the population are exhibiting reactions, such as allergies, to the negative health-related effects of these construction products. natureplus therefore evaluates the compatibility of construction products, especially in the usage phase, according to strict standards in order to actively promote those materials which pose no risk to health and are, in addition, conducive to a healthy room climate.

The natureplus®-Eco-label is an award for construction products which meet the highest standards of sustainability by exhibiting the best possible performance in terms of the environment, health and functionality. Scope of the assessment is the building material as raw material and as component. Only the best products in a particular product group are eligible for certification in order to act as an orientation for all building professionals and consumers towards the promotion of a culture of sustainable building. The natureplus®-Eco-label has anticipated the requirements of construction products of the European Construction Products Directive EU CPR 305/2011: In the future this regulation requires a declaration of performance with evidence of the sustainable use of natural resources and of compliance with requirements in terms of low impact, over their entire life cycle, on the environmental quality or on the climate, energy-efficiency and the hygiene, health and safety of people. The natureplus®-Eco-label already provides these proofs of performance in relation to the essential characteristics of construction products. This is gauged by natureplus according to criteria and requirements which, as a rule, far exceed the legal requirements and as a minimum comply in each case with the strictest recognised standards applicable.

The natureplus®-Eco-label is classified as a Type I environmental label as per ISO 14024, taking into consideration the EU Ecolabel Regulation and the EMAS regulation on environmental auditing, and is valid across the whole of Europe according to uniform criteria. The pre-requirements for a construction product to be certified with the natureplus®-Eco-label are its especially high performance characteristics in terms of the environment, health and sustainability. The main focuses are on the protection of limited resources by the minimisation of the use of petrochemical substances, sustainable raw material extraction/harvesting, resource-efficient production methods and the longevity of the products. Therefore, building products made from renewable raw materials, raw materials which are unlimited in their availability or from secondary raw materials will be favoured for certification.

I Application Areas

The following criteria contain the requirements for the award of the natureplus® eco-label for bricks and blocks filled with insulation material. These products are a combination of two products that can each be awarded the natureplus® eco-label. The award guideline is to be applied exclusively to products of the stated combination.

2 Award Criteria

The prerequisite for a product to be awarded the natureplus® quality label in accordance with these guidelines is compliance with the following award guidelines:

- GL-5001 Chemicals Directive
- GL-5003 Nature Conservation when Exploiting Mineral Resources
- GL-5004 Transparency and Social Responsibility
- GL-5010 Low-emission building products
- GL-5020 Climate compatibility and energy efficiency

2.1 Functional Suitability

The manufacturer provides information about technical and physical characteristics of the product and specifies the standards, test procedures and methods used to determine these properties. If the applied standards contain requirements for the products, it is to be clearly indicated whether they are met.

The product meets the requirements for the suitability of application by holding the state-specific or the European technical approval.

The product must fulfil the following requirement for thermal transmittance calculated in accordance with the current, applicable European standards:

- Thermal transmittance (U-Wert): $\leq 0.2 \text{ W/m}^2\text{K}$

If the product does not meet the requirement(s) for thermal transmittance, it must be clearly stated on the product packaging and in the technical data sheets that further measures are necessary in order to achieve the required insulating effect.

The fire behaviour of the product must correspond at least to building material class E according to EN 13501-1.

In case the product is supplied to countries in which other requirements apply as the ones in the standards mentioned so far, these requirements must be met as well. The manufacturer states the countries where the product is distributed and provides official certification by approved testing institutions to confirm compliance with the requirements.

2.2 Composition, Forbidden Substances, Substance Restrictions

Bricks and blocks filled with integrated insulation must be made to at least 99% from the basic components masonry and insulation.

The use of additional additives, up to 1 M-%, is only permissible if they are necessary to anchor/bind the insulation material within the brick/block. These additives must fulfil the requirements of the Chemicals Directive GL-5001. The use of such additives may require that additional laboratory tests must be conducted, in accordance with Section 3 of this guideline.

In order to evaluate these additives, a full declaration of the input components must be provided.

For construction blocks filled with insulation, in accordance with GL-0401, only the exclusive use of inorganic additives is permitted.

2.3 RawMaterial Sourcing, Production of Preliminary Products, Production

The requirements for raw material sourcing and production of prefabricated products are addressed in the guidelines for the prefabricated products.

The manufacturer must demonstrate that for the protection of employees, a system of management for hazardous substances which conforms to national standards and legal regulations is in place at the production facility. Information on dust release and compliance with general dust limit values must be included therein. Where compliance with the general dust limit values or other occupational limit values cannot be guaranteed, despite technical and organisational measures, personal protection equipment must be made available. The employer must take measures to minimize the levels of avoidable exposure to the employees to harmful substances.

2.4 Usage

The product must not exhibit any unpleasant or foreign smells or odours during use.

The emissions during use must comply with the threshold values according to section 3.

2.5 Recycling/ Disposal

A disposal concept for the products must be presented and must contain details on the system for component separation and recycling. Disposal at an inert materials disposal site/facility according to the "Decision of the EU council of the 19th December 2002 on the definition of criteria and procedures for the receipt and acceptance of waste products at waste disposal sites according to article 16 and appendix 2 of the guideline 1999/31/EC" is permitted for mineral components. If this is not possible, alternative disposal procedures must be specified by the manufacturer.

2.6 Ecological Parameters

All products in this product group must be manufactured in such a way that the ecological parameters listed in RL 5020 are fulfilled.

2.7 Declaration

The product packaging should display a full declaration of the input materials listed, analogue to the EU-Cosmetic Regulations, according to the declining mass percentage. If it is not possible to display this information directly on the product packing, it should be provided with the product in a technical datasheet or sales leaflet (in English or in the national language). If intermediate/preliminary products or formulations are used as input substances and the proportion present in the final product is >0.1 M-%, then all the substances used within these must also be taken into account for the declaration.

For naming the input materials as part of the declaration the following applies:

- More than 1 M-% - designation of the substance in question
- Less than 1 M-% - at least a functional designation (e.g. "moth proofing agent")

Furthermore, it is obligatory to provide the following information in a suitable form to the consumer or user (eg. online):

- Instructions for use and safety precautions
- Indications for storage and disposal
- Batch numbers
- City/town and country of production
- Indication of geographical origin of the key input material

When using ingredients with an environmentally hazardous potential, the manufacturer must indicate at an appropriate place which measures are to be taken within the framework of dismantling and demolition work to protect the environment (e.g. controlled dismantling).

Additionally, the following product-specific information must be made available to the consumer or user.

- Labelling according to the guidelines of the European Community (Communauté Européenne, CE marking) or the respective general technical approval, including a scope specification
- Apparent density in kg/m^3
- Thermal nominal value λ_D according to EN ISO 10456 or an equivalent standard
- Thermal design value λ_R according to EN ISO 10456 or an equivalent standard
- Type and field of application, i.e. as per DIN 4108, Austrian standard ÖNORM B 6000
- Fire performance Euro class according to EN 13501-1

2.8 Processing and Installation

The manufacturer must recommend a natureplus-certified mortar for use in the installation/ application of the product. If such a mortar is not available, at least one low-emission mortar based on mineral compounds is to be recommended. This mortar must not contain more than a maximum of 5 M-% organic components and a maximum of 0.1 M-% volatile organic compounds. This is subject to testing based on the full declaration of all input materials, supplemented with information supplied by the manufacturer of the mortar.

The following additives are prohibited:

- Glycol ethers and -esters
- APEO's (Alkyl phenol ethoxylate)
- Formaldehyde separators/dispersers
- Halogen organic compounds

The manufacturer must demonstrate whether working procedures avoiding dust release are available for the processing of the product. If this is the case, these procedures are to be recommended and suitably presented within the processing guidelines. If compliance with the general dust limit values might not be guaranteed, wearing personal protection equipment must be recommended.

2.9 Packaging

The packaging used must be recyclable. The manufacturer must belong to a recycling system, if one exists for the corresponding material.

Paper and cardboard packaging must be made from recycled paper. Alternatively, paper from sources as per GL-5002 is also permitted.

Plastic packaging must be made from polyolefins. PET, polystyrene or polycarbonates are allowed exceptionally in reasonable cases.

PVC packaging is generally not permitted.

Packaging must not contain biocides.

The natureplus certification mark has to be printed on the packaging after it has been awarded.

3 Laboratory Tests

The products are subject to laboratory analyses to test for harmful substances and undesirable ancillary ingredients. A representative sample is collected during the production audit. If the sample collection cannot be conducted by a natureplus examiner, an independent person designated by natureplus can collect the sample. For products with different sizes but the same composition, a single sample is sufficient.

3.1 Volatile Organic Compounds VOC / TVOC

To check the emission of VOC and to determine the TVOC and TSVOC, an emission chamber test is carried out with the product. Measurements are usually performed after 3 and 28 days. If a low VOC emission is to be expected, a termination measurement can also be carried out after 7 days. The test-chamber examination is performed according to the current version of natureplus guideline 5010. The product must comply with the limit values specified in guideline 5010.

3.2 Element Analyses

There are no further requirements that make element analyses necessary.

3.3 Other Analyses

Halogenic organic compounds

Test parameters	Limit values	Unit	Method
Halogenic organic compounds: AOX/EOX	≤ 1	mg/kg	TM-03 Halo

Odour

Test parameters	Limit values	Unit	Method
Odour	≤ 3	Odour intensity	TM-04 Odour

4 Appendix

Test methods

TM-01 VOC : Volatile Organic Compounds VOC/TVOC, formaldehyde, acetaldehyde and TSVOC: DIN EN ISO 16000 series expanded by the natureplus implementation rules.

TM-02 Metals: ICP-MS measurements according to DIN EN ISO 17294-2, supplemented with the natureplus implementation rules and a sample preparation adjusted to the issue analysed.

TM-03 Halo: Halogenic organic compounds after combustion, determined by microcoulometry according to the natureplus implementation rules "AOX/EOX".

TM-04 Odour: natureplus implementation rules "odour intensity", 6-degree grading scale 24h after loading the test chamber

TM-05 Pesticides: DFG S 19 extended by natureplus implementing regulations

TM-08 Foreign fibres and foreign substances: scanning electron microscopy SEM

TM-09 Monomeric isocyanates: 24h after test chamber loading

