natureplus e.V.

Guideline 0408

Perlite Boards for Internal Applications

Version: Oct. 23, 2026
for the awardance of the eco-label

Introduction

The International Association for Sustainable Building and Living - natureplus association - pursues the goal of promoting sustainable building products and increasing their popularity and use. To this end, sustainability criteria for building products are defined and verified as part of regular conformity assessments at the applicant's premises.

Three comprehensive sustainability definitions are created to achieve a holistic understanding of quality.

CLIMATE PROTECTION

The climate crisis is worsening, and the consequences are becoming increasingly visible. The construction sector is one of the largest emitters, accounting for around 40% [1] of global greenhouse gas emissions. Energy-intensive manufacturing processes, long transport routes and short renovation cycles are often still characteristic of the status quo.

The natureplus certification requires manufacturers to meet limit values on CO2 emissions and primary energy consumption.

[1] UNEP, 2020, 2020 Global Status Report for Buildings and Construction, p. 4.

HEALTHY LIVING

In Western societies, we spend about 90% [2] of our lives in buildings. Pollutants emitted by building materials can accumulate in the indoor air we breathe daily, posing unnecessary health risks to occupants. The accumulation of chemical pollutants from building materials in household dust is also a cause for concern.

The natureplus certification ensures that hazardous input materials are avoided or used in quantities that are harmless to health. Emissions from building products are strictly regulated and regularly monitored.

[2] Umweltbundesamt, o. D., Ausschuss für Innenraumrichtwerte (AIR)

CONSERVATION OF RESOURCES

All construction activities have an impact on nature and the environment, with the consumption of finite resources remaining unacceptably high. The production of building materials in Germany consumes about 60% of our resources, and as much as 90% if only mineral raw materials are considered. At the same time, the construction sector is responsible for 50% of the waste generated. [3]

The natureplus certification sets out requirements for increased transparency in the supply chain, respect for human rights and the environment, and the responsible use of resources throughout the life cycle of a building product.
Sustainable materials should also be durable, reusable, or recyclable.

[3] VDI ZRE, 2019, Ressourceneffizienz im Bauwesen – Von der Planung bis zum Bauwerk, p. 5.

Notes on this product guideline:

The eco-label, the certification programme including all associated documents is the property of the non-profit natureplus® environmental organisation. The Association and its specially appointed Criteria Commission are therefore responsible for the further development of the requirements.

The label is awarded by the European cooperative natureplus Institute SCE mbH.

In the event of textual discrepancies between different language versions of a guideline, the Criteria Commission's Task Force will determine the valid wording. The affected language versions will be amended to reflect the valid wording.

In the event of conflict between the basic guidelines (50XX) and this product guideline, the product award guideline shall prevail.

For questions, criticism and suggestions, please contact:

International Association for Sustainable Building and Living - natureplus association
Hauptstr. 24, 69151 Neckargemünd, Germany
criteria@natureplus.org
+49 (0)6223 866 017 0

1 Application Areas

The following criteria contain the requirements for the awardance of the natureplus eco-label for perlite boards for internal application. The award guideline is to be applied exclusively to those products mentioned in this guideline.

2 Award Criteria

The prerequisite for a product to be awarded the natureplus® quality label in accordance with these guidelines is compliance with the following award guidelines:

- GL5001 Chemicals Directive

The prerequisite for a product to be awarded the natureplus quality label is compliance with the basic criteria RL-0000 and the chemicals directive RL-5001.

- GL-5003 Nature Conservation when Exploiting Mineral Resources
- GL5004 Transparency and Social Responsibility
- GL5010 Low-emission building products
- GL5020 Climate compatibility and energy efficiency

2.1 Functional Suitability

The manufacturer must declare the following building physics characteristic values:

- Water vapour diffusion resistance factor μ in accordance with EN 12086
- Water absorption coefficient AW in accordance with EN ISO 15148

The thermal nominal value at 23°C and 50% humidity as per the corresponding European standards must comply with the following requirements:

- Insulation not subject to pressure load $\lambda_{23,50} \leq 0{,}045$ W/mK
- Insulation functioning as plaster base $\lambda_{23,50} \leq 0{,}055$ W/mK
- Insulation subject to pressure load $\lambda_{23,50} \leq 0{,}065$ W/mK

The manufacturer must provide proof in the form of appropriate test assessments. The cement employed must comply with EN 197 or a comparable standard. The product must be classified as non-flammable (class A1 and A2-s1,d0 according to EN 13501).

2.2 Composition, Forbidden Substances, Substance Restrictions

The following components are permitted: expanded Perlite, binding agents made from mineral or renewable raw materials. The use of other types of binding agents or additives must be technicallyjustified.

The product must consist of at least 97% mineral-based components based upon the dry weight of the product.

Halogenic organic compounds and polyurethane are not permitted.

The product is subject to laboratory analyses as laid down in section 3 and has to comply with the limit values stated therein.

2.3 Raw Material Sourcing, Production of Preliminary Products, Production

The extraction of mineral raw materials must be in compliance with the requirements as laid downin GL-5003.

The manufacturer must demonstrate that a hazardous substance management according to national standards and regulations is available at the production facility for employee protection. Information on dust release and compliance with general dust limit values must be included therein. Where compliance with the general dust limit values or other occupational limit values cannot be guaranteed despite technical and organisational measures, personal protection equipment must be available. It must be aimed for a minimisation of avoidable burdens of the employees.

If the product contains more than 5% cement, the cement manufacturer must provide confirmation that the following requirements have been met:

- The cement production equipment must meet modern standards for energy efficiency of the ovens and for the flue gas cleaning equipment.
- If waste products are also incinerated, then the emissions must comply with the Directive 2000/76/EC of 4. December 2000 concerning the incineration of waste

- Point II.1 “Special Regulations for Cement Ovens in which Waste Products are Incinerated”

2.4 Usage

The product must not exhibit any unpleasant or foreign smells or odours.

The emissions during use have to be in compliance with the limit values according to section 3.

2.5 Reuse, recycling and disposal

The components must be suitable for disposal in a landfill for inert waste according to the “Decision of the EU council of the 19th December 2002 on the definition of criteria and procedures for the receipt and acceptance of waste products at waste disposal sites according to article 16 and appendix 2 of the guideline 1999/31/EG” and according to the procedures applied by the Member States. The manufacturer must provide evidence of compliance with the Member State's implementation regulation (e.g. approval document by national authorities or laboratory tests).

2.6 Ecological Parameters

All products in this product group must be manufactured in such a way that the environmental parameters listed in RL5020 are complied with.

2.7 Public Declaration

The product packaging should display a full declaration of the input materials listed, analogue to the EU-Cosmetic Regulations, according to the declining mass percentage. If it is not possible to display this information directly on the product packing, it should be provided with the product in a technical datasheet or sales leaflet (in English or in the national language). If intermediate/preliminary products or formulations are used as input substances and the proportion present in the final product is >0.1 M-%, then all the substances used within these must also be taken into account for the declaration.

For naming the input materials as part of the declaration the following applies:

- More than 1 M-% - designation of the substance in question
- Less than 1 M-% - at least a functional designation (e.g. “moth proofing agent“)

Furthermore, it is obligatory to provide the following information in a suitable form to the consumer or user (eg. online):

- Instructions for use and safety precautions
- Indications for storage and disposal
- Batch numbers
- City/town and country of production
- Indication of geographical origin of the key input material

When employing components with a potential for environmental hazard, the manufacturer has to suitably indicate measures to be taken to ensure environmental protection during removal and demolition (i.e. controlled deconstruction).

Additionally, the following product-specific information must be made available to the consumer or user.

- Labelling according to the guidelines of the European Community (Communauté Européenne, CE marking) or the respective general technical approval, including a scope specification
- General data according to corresponding European standards or indications about product characteristics
- Density ρ [kg/m³]
- Indications about the product's fire behaviour

2.8 Processing and Installation

The manufacturer must provide qualified installation and handling instructions, in particular on methods to avoid thermal bridges. The documentation must also contain construction examples for a condensation-free and thermal-bridge-free installation of the components.

If it is necessary to employ an adhesive during the handling/installation process, the manufacturer must recommend a natureplus certified product or a very low emission adhesive, where possible amineral-based adhesive, in accordance with the requirements of the Committee for Health-relatedevaluation of Building Products

(AgBB), EMICODE EC1 or a comparable standard (e.g. “Blauer Engel“ – the Blue Angel environmental quality label).

The recommended adhesive must not contain any of the following additives:

- Glycol ethers and esters
- APEO's (alkylphenol ethoxylates)
- Halogenated Isothiazolinone
- Formaldehyde decomposition agents

The manufacturer must demonstrate whether working procedures avoiding dust release are available for the processing of the product. If this is the case, these procedures are to be recommended and suitably presented within the processing guidelines. If compliance with the general dust limit values might not be guaranteed, wearing personal protection equipment must be recommended.

2.9 Packaging

The packaging used must be recyclable. The manufacturer must be participate in a recycling system if there is one for the corresponding material.

Paper and cardboard packaging must be made from recycled paper. Alternatively, paper from sources as per GL-5002 is permitted.

Plastic packaging must be comprised from polyolefins. PET, polystyrene or polycarbonates are allowed exceptionally in reasonable cases. Packaging made from PVC is generally not permitted.

Packaging must not contain biocides.

The natureplus certification mark has to be printed on the packaging after the awardance of the product.

3 LaboratoryTests

The products are subject to laboratory analyses to test for harmful substances and undesirable ancillary ingredients. A representative sample is collected during the production audit. If the sample collection cannot be conducted by a natureplus examiner, an independent person designated by natureplus can collect the sample. For products with different sizes but the same composition, a single sample is sufficient.

3.1 Volatile Organic Compounds VOC / TVOC

To check the emission of VOC and to determine the TVOC and TSVOC, an emission chamber test is carried out with the product. Measurements are usually performed after 3 and 28 days. The test-chamber examination is performed according to the current version of natureplus guideline 5010. The product must comply with the limit values specified in guideline 5010.

3.2 Element Analyses

The product is subject to an element analysis to determine the content of harmful elements and to check for undesirable contaminations. The measurements have to be in compliance with the limit values. The analysis is performed according to the current version of the test method TM-02 metals.

An eluate analysis is mandatory if the required values of the content analysis are not met.

Element	Limit value [mg/kg]
Arsenic (As)	≤ 10
Cadmium (Cd)	≤ 1
Cobalt (Co)	≤ 20
Chromium (Cr)	≤ 50
Copper (Cu)	≤ 35
Mercury (Hg)	≤ 0,5
Nickel (Ni)	≤ 20
Lead (Pb)	≤ 15
Antimon (Sb)	≤ 5
Tin (Sn)	≤ 5

3.3 Other Analyses

Chromium VI

Test parameters	Limit values	Unit	Method
Chromium VI (Cr VI)	≤ 2	mg/kg	TRGS 613

Halogenic organic compounds

Test parameters	Limit values	Unit	Method
Halogenic organic compounds: AOX/EOX	≤ 1	mg/kg	TM-03 Halo

Odour

Test parameters	Limit values	Unit	Method
Odour	≤ 3	Odour intensity	TM-04 Odour

4 Appendix

Test methods

TM-01 VOC : Volatile Organic Compounds VOC/TVOC, formaldehyde, acetaldehyde and TSVOC: DIN EN ISO 16000 series expanded by the natureplus implementation rules in guideline 5010.

TM-02 Metals: ICP-MS measurements according to DIN EN ISO 17294-2, supplemented with the natureplus implementation rules and a sample preparation adjusted to the issue analysed.

TM-03 Halo: Halogenic organic compounds after combustion, determined by microcoulometry according to the natureplus implementation rules "AOX/EOX".

TM-04 Odour: natureplus implementation rules "odour intensity", 6-degree grading scale 3 days after loading the test chamber following VDA 270:2018.

TM-05 Pesticides: DFG S 19 extended by natureplus implementing regulations

TM-08 Foreign fibres and foreign substances: scanning electron microscopy SEM

TM-09 Monomeric isocyanates: 24h after test chamber loading

TM-10 PAH: HPLC / GC-MS, sum according to EPA